

CreatorGloss Art

EN

Coated Paper 2 Sides Gloss

| Property | | | Unit | Tolerance | | | | | | | | | | |
|-----------------------|------------|------------|------|-----------|------|------|------|-----|-----|-----|-----|-----|-----|--|
| Substance | ISO 536 | TAPPI T410 | gsm | ± 4% | 115 | 135 | 150 | 170 | 200 | 250 | 300 | 350 | 400 | |
| Thickness | ISO 534 | TAPPI T411 | µm | ± 4% | 87 | 103 | 109 | 125 | 149 | 191 | 234 | 288 | 330 | |
| Brightness R457 D65 | ISO 2470-2 | - | % | ± 2 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | |
| Whiteness CIE D65/10° | ISO 11475 | - | - | ± 3 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | |
| Opacity | ISO 2471 | TAPPI T519 | % | -2.0 | 93 | 95,5 | 96 | 97 | - | - | - | - | - | |
| Smoothness Bekk | ISO 5627 | TAPPI T479 | s | ±30% | 1000 | 1000 | 1000 | 850 | 600 | 500 | 350 | 350 | 200 | |
| Relative Humidity | - | TAPPI T502 | % | ± 7 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | |

- Last updated: **15-02-16**
- Values are subject to change without notice.

ES

Estucado 2 Caras Brillante

| Propiedad | | | Unidades | Tolerancia | | | | | | | | | | |
|----------------------|------------|------------|----------|------------|------|------|------|-----|-----|-----|-----|-----|-----|--|
| Gramaje | ISO 536 | TAPPI T410 | gsm | ± 4% | 115 | 135 | 150 | 170 | 200 | 250 | 300 | 350 | 400 | |
| Calibre | ISO 534 | TAPPI T411 | µm | ± 4% | 87 | 103 | 109 | 125 | 149 | 191 | 234 | 288 | 330 | |
| Brightness R457 D65 | ISO 2470-2 | - | % | ± 2 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | |
| Blancura CIE D65/10° | ISO 11475 | - | - | ± 3 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | |
| Opacidad | ISO 2471 | TAPPI T519 | % | -2.0 | 93 | 95,5 | 96 | 97 | - | - | - | - | - | |
| Lisura Bekk | ISO 5627 | TAPPI T479 | s | ±30% | 1000 | 1000 | 1000 | 850 | 600 | 500 | 350 | 350 | 200 | |
| Humedad relativa | - | TAPPI T502 | % | ± 7 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | |

- Última actualización: **15-02-16**
- Los valores están sujetos a cambio sin aviso previo.

FR

Couché 2 Faces Brillant

| Propriété | | | Unité | Tolérance | | | | | | | | | | |
|-----------------------|------------|------------|-------|-----------|------|------|------|-----|-----|-----|-----|-----|-----|--|
| Grammage | ISO 536 | TAPPI T410 | gsm | ± 4% | 115 | 135 | 150 | 170 | 200 | 250 | 300 | 350 | 400 | |
| Épaisseur | ISO 534 | TAPPI T411 | µm | ± 4% | 87 | 103 | 109 | 125 | 149 | 191 | 234 | 288 | 330 | |
| Blancheur R457 D65 | ISO 2470-2 | - | % | ± 2 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | |
| Blancheur CIE D65/10° | ISO 11475 | - | - | ± 3 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | |
| Opacité | ISO 2471 | TAPPI T519 | % | -2.0 | 93 | 95,5 | 96 | 97 | - | - | - | - | - | |
| Lissé Bekk | ISO 5627 | TAPPI T479 | s | ±30% | 1000 | 1000 | 1000 | 850 | 600 | 500 | 350 | 350 | 200 | |
| Humidité relative | - | TAPPI T502 | % | ± 7 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | |

- Dernière actualisation : **15-02-16**
- Ces valeurs peuvent être modifiées sans avis préalable.

IT

Carta Patinata Lucida

| Proprietà | | | Unità | Tolleranza | | | | | | | | | | |
|--------------------|------------|------------|-------|------------|------|------|------|-----|-----|-----|-----|-----|-----|--|
| Grammatura | ISO 536 | TAPPI T410 | gsm | ± 4% | 115 | 135 | 150 | 170 | 200 | 250 | 300 | 350 | 400 | |
| Spessore | ISO 534 | TAPPI T411 | µm | ± 4% | 87 | 103 | 109 | 125 | 149 | 191 | 234 | 288 | 330 | |
| Bianco R457 D65 | ISO 2470-2 | - | % | ± 2 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | |
| Bianco CIE D65/10° | ISO 11475 | - | - | ± 3 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | |
| Opacità | ISO 2471 | TAPPI T519 | % | -2.0 | 93 | 95,5 | 96 | 97 | - | - | - | - | - | |
| Liscio Bekk | ISO 5627 | TAPPI T479 | s | ±30% | 1000 | 1000 | 1000 | 850 | 600 | 500 | 350 | 350 | 200 | |
| Umidità relativa | - | TAPPI T502 | % | ± 7 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | |

- Ultima revisione: **15-02-16**
- I valori sono soggetti a modifiche senza preavviso.

PT

Couché 2 Faces Brilhante

| Propriedade | | | Unidade | Tolerância | | | | | | | | | | |
|-------------------|------------|------------|---------|------------|------|------|------|-----|-----|-----|-----|-----|-----|--|
| Gramagem | ISO 536 | TAPPI T410 | gsm | ± 4% | 115 | 135 | 150 | 170 | 200 | 250 | 300 | 350 | 400 | |
| Calibre | ISO 534 | TAPPI T411 | µm | ± 4% | 87 | 103 | 109 | 125 | 149 | 191 | 234 | 288 | 330 | |
| Brancura R457 D65 | ISO 2470-2 | - | % | ± 2 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | |
| Brancura CIE | ISO 11475 | - | - | ± 3 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | |
| Opacidade | ISO 2471 | TAPPI T519 | % | -2.0 | 93 | 95,5 | 96 | 97 | - | - | - | - | - | |
| Lisura Bekk | ISO 5627 | TAPPI T479 | s | ±30% | 1000 | 1000 | 1000 | 850 | 600 | 500 | 350 | 350 | 200 | |
| Humidade relativa | - | TAPPI T502 | % | ± 7 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | |

- Última actualização: **15-02-16**
- Os valores estão sujeitos a mudanças sem pré-aviso.

