

## TINTS 80GR

---

Parameters	Standard Used	Units	Measured
Substance	ISO 536	g/m <sup>2</sup>	80 +/- 2
Thickness	ISO 534	µm	104 +/- 3
Bulk	ISO 534		1,3
Moisture	ISO 287	%	
Smoothness	ISO 8791	Bendtsen ml/min	220 +/- 50
Formation	Kajaani	Kajaani Index	
Whiteness	ISO 11475	CIE	
Opacity	ISO 2471	%	
Stiffness	ISO 2493	m/N	105 +/- 15 (MD) 50 +/- 15 (CD)
Porosity			

### References:

- \* ISO 14001 - Environmental
  - \* ISO 18001 - OHSAS - Health & Safety
  - \* ISO 9001:2000 - Quality Systems
  - \* ISO 9706 - Ageing Resistance
-

## TINTS 160GR

---

Parameters	Standard Used	Units	Measured
Substance	ISO 536	g/m <sup>2</sup>	160 +/- 4
Thickness	ISO 534	µm	202 +/- 4
Bulk	ISO 534		1,26
Moisture	ISO 287	%	
Smoothness	ISO 8791	Bendtsen ml/min	220 +/- 50
Formation	Kajaani	Kajaani Index	
Whiteness	ISO 11475	CIE	
Opacity	ISO 2471	%	
Stiffness	ISO 2493	m/N	650 +/- 50 (MD) 370 +/- 40 (CD)
Porosity			

### References:

- \* ISO 14001 - Environmental
  - \* ISO 18001 - OHSAS - Health & Safety
  - \* ISO 9001:2000 - Quality Systems
  - \* ISO 9706 - Ageing Resistance
-